

## Technical Data Sheet

# Virtuo Epoxy Top Coat Finish

## Epoxy Top Coat Finish

### Product Description

A two component, polyamide cured glossy epoxy coating specially formulated as an Finish coat that needs to be applied over any primed surface to give the desired glossy and tough finish.

### Recommended Use

It is recommended as tough, hard wearing coating on properly primed surface. It is recommended as universal epoxy topcoat in general industries for Structures, Concrete, Equipments, Machineries, Storage Tanks etc. This product is recommended in Power Plants, Transmission lines, Infrastructure projects, Bridges, Chemical Plants, Food & Pharmaceutical Plants, Mining & Steel Plants, and Petrochemicals Plants etc.

### Physical Data

Color	: Any (IS/RAL/Fan deck)
Finish	: Glossy
Solid by Volume	: 48 ± 2%
Supply Weight (Kg/ Ltr)	: 1.15±0.05
Flash Point	: 29° C
Dry Heat Resistance	: Intermittent: 120°C, Continuous: 100°C
Shelf Life	: 12 months

### Film Thickness

#### Recommended film thickness per coat

Dry Film Thickness	: 40μ to 60μ in single coat
Wet Film Thickness	: 90-120μ in single coat
Theoretical Coverage Rate	: 7.5 sq.mt / lit at recommended DFT of 70μ

### Surface Preparation

All surfaces to be coated should be clean, absolutely dry and oil or moisture free before painting application. Oil and grease should be removed by solvent cleaning.

**Repair Cases:** Corroded areas should be power tool cleaned to St3 or blast cleaned to Sa2 or better. Existing system should be dry and free from loose paint, salt, grease and other contaminants prior to over coating.

**New steel:** Abrasive blasting to Sa 2½ (ISO 8501-1:2007). For temporary protection, if required, use a suitable shop primer. All damage of shop primer and contamination from storage and fabrication should be thoroughly cleaned prior to final painting.

**Maintenance:** Remove oil and grease etc. thoroughly with suitable detergent. Remove salts and other contaminants by high pressure fresh water cleaning. Clean damaged areas thoroughly by power tool cleaning to St 3 (ISO 8501-1:2007) (minor areas) or by abrasive blasting to min. Sa 2, preferably to Sa 2½ (ISO 8501-1:2007). Improved surface preparation will improve the performance of the product.

**Stainless steel:** To be abrasive blast cleaned to a uniform, sharp, dense profile (ISO Comparator Medium (G), corresponding to Rz minimum 50 micron. Any salts, grease, oil, etc. to be removed before abrasive blasting is commenced.

## Application Data

<b>Application Method</b>	Spray/ Airless Spray/Brush/ Roller
<b>Mixing Ratio</b>	3 Part (Base) : 1 Part (Hardener)
<b>Pot Life</b>	Four Hours at 30°C
<b>Thinner and Cleaner</b>	Virtuo Epoxy Thinner
<b>Airless Nozzle Orifice</b>	0.45 - 0.58mm
<b>Nozzle Pressure</b>	176 kg/cm <sup>2</sup> or 2500 psi

**Working Precautions:** Material should not be allowed to remain in pipeline, hoses, gun or spray equipment. Thoroughly flush all equipment with Universal Thinner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages, the work should recommence with freshly mixed units.

**Maintenance:** Clean all equipment immediately after use with Universal Thinner. It is good working practice to periodically flush out spray equipment during the course of the working day. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

---

## Drying Characteristics

Surface Dry	: 40-45 mins
Touch Dry (to Handle)	: 3 Hours
Hard Dry	: 24 Hours
Over coating Interval	: Minimum 3 Hours

Drying and curing times are determined at 30°C under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

## Compatibility

Previous Coating	: Epoxy Primers, Epoxy MIO
Subsequent Coating	: Epoxy, Polyurethanes, Modified Alkyds

## Storage

This is solvent based coating and the containers should be kept in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed.

## Caution

This product is for professional use only. The paint applicators should be trained experienced and have the capability and equipment to mix and apply the coatings correctly as instructed. Applicators should use appropriate protection equipment when using this product.

This is solvent based product and should be use under well ventilated conditions. Do not inhale spray mist. Skin contact should be avoided. In case of spillage on the skin, it should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water.